


101FR M³ AWAPLAN PREMIUM FR

INSULATED DECKS



Material Requirements	
TAMKO BASE-N-PLY®	
Fiberglass Sheet	1 ply
TAMKO AWAPLAN PREMI	UM FR
(Granule Surfaced)	1 ply
Asphalt (Per 100 sq. ft.)	Approx. 23 lbs
M ³ Adhesive (Per 100 sq. ft.)	Approx. 1-1/2 to 2-1/2 gal.

Slope: Positive drainage up to 3 in. per linear ft. **For slopes above 3/4 in. per linear ft.,** fastening of the AWAPLAN PREMIUM FR is required.

Deck: The deck should conform to TAMKO general requirements.

Insulation: The insulation should be installed according to the manufacturer's specification in the thickness required. The insulation should conform to TAMKO requirements. Polyisocyanurate and expanded polystyrene must have an overlay of a minimum 1/2 in. fiberboard, perlite, or fiberglass roof insulation.

Asphalt: The asphalt should be certified by the manufacturer to meet ASTM D-312, Type III for slopes up to 1/4 in. and Type IV for slopes up to 3 in.

Adhesive: The adhesive **must** be TAM-PRO® M³ Adhesive.

BASE-N-PLY: Starting at the low point of the roof, install 1 layer of TAMKO BASE-N-PLY beginning with a 1/2 m width, then a full 1 m width, side lapped 2 in. and end lapped 4 in. Apply at a right angle to the slope of the roof. Solid mop to the insulation with approximately 23 lbs. (±15%) of specification asphalt per 100 sq. ft.

AWAPLAN PREMIUM FR: Starting at the low point of the roof, install 1 layer of TAMKO AWAPLAN PREMIUM FR granule surfaced sheet, side lapped 4 in. and end lapped 6 in. The AWAPLAN PREMIUM FR should be solidly adhered to the base ply with an application of M³ Adhesive at a rate not to exceed 1-1/2 to 2 gal. per sq. for squeegee application and 1-1/2 to 2-1/2 gal. per sq. for spray application. Side laps and end laps shall be heat welded together. **Use care when applying heat as damage can occur to the product by overheating.**

Using a 3/16" serrated edge squeegee will achieve an application rate of 1-1/2 gal. per sq. For spray application, the M³ Adhesive must be a minimum of 100°F at the spray tip. M³ Adhesive should not be heated above 180°F.

Caution should be used when exposing M³ Adhesive to an open flame.

Flashing: The flashing material **must** be a TAMKO polyester reinforced modified asphalt flashing material.

U. L. Requirements:

Contact TAMKO for information on U.L. systems requirements.

Caution: A product(s) in this specification contains crystalline silica and formaldehyde. Crystalline silica and formaldehyde have been classified as "known" human carcinogens by the International Agency for Research on Cancer (IARC) and the National Toxicology Program. A product(s) in this specification also contains oxidized asphalt. Occupational exposures to oxidized asphalt and its emissions during roofing have been classified by IARC as a "probable human carcinogen". Oxidized asphalt also contains Polycyclic Aromatic Hydrocarbons some of which have been classified by IARC as known or probable human carcinogens. The physical



101FR M³ AWAPLAN PREMIUM FR


INSULATED DECKS

nature of the product(s) in this specification may help limit any inhalation or dermal hazard during application and/or removal. However, physical forces such as sawing, grinding or drilling during demolition work and heating or burning may increase the inhalation or dermal exposure hazard of the product(s) in this specification. Take precautions to prevent breathing and contact with skin.



102FR M³ AWAPLAN PREMIUM FR

INSULATED DECKS



Material Requirements

TAMKO TAM-GLASS PREMIUM® or TAM-PLY IV® Fiberglass Ply Sheet 2 plies

TAMKO AWAPLAN PREMIUM FR
(Granule Surfaced) 1 ply

Asphalt (Per 100 sq. ft.) Approx. 46 lbs.

M³ Adhesive (Per 100 sq. ft) Approx. 1-1/2 to 2-1/2 gal.

Slope: Positive drainage up to 3 in. per linear ft. **For slopes above 3/4 in. per linear ft.,** fastening of the AWAPLAN PREMIUM FR is required.

Deck: The deck should conform to TAMKO general requirements.

Insulation: The insulation should be installed according to the manufacturer's specification in the thickness required. The insulation should conform to TAMKO requirements. Polyisocyanurate and expanded polystyrene must have an overlay of a minimum 1/2 in. fiberboard, perlite, or fiberglass roof insulation.

Asphalt: The asphalt should be certified by the manufacturer to meet ASTM D-312, **Type III for slopes up to 1/4 in.** and **Type IV for slopes up to 3 in.**

Adhesive: The adhesive **must** be TAM-PRO[®] M³ Adhesive.

Fiberglass Ply Sheet 2 Ply Installation: Over the insulation, install 2 plies of TAM-GLASS PREMIUM or TAM-PLY IV inspecification asphalt. Starting from the low point of the roof, apply a 1/2 m width, then a full 1 m width. Follow with full 1 m widths, shingle fashion, lapping each ply 20-11/16 in. in such a manner so that at least 2 plies cover the insulation at any one point. Approximately 23 lbs. (±15%) of specification asphalt per 100 sq. ft. should be used to embed each ply.

AWAPLAN PREMIUM FR: Starting at the low point of the roof, install 1 layer of TAMKO AWAPLAN PREMIUM FR granule surfaced sheet, side lapped 4 in. and end lapped 6 in. The AWAPLAN PREMIUM FR should be solidly adhered to the ply sheet with an application of M³ Adhesive at a rate not to exceed 1-1/2 to 2 gal. per sq. for squeegee application and 1-1/2 to 2-1/2 gal. per sq. for spray application. Side laps and end laps shall be heat welded together. **Use care when applying heat as damage can occur to the product by overheating.**

Using a 3/16" serrated edge squeegee will achieve an application rate of 1-1/2 gal. per sq. For spray application, the M³ Adhesive must be a minimum of 100°F at the spray tip. M³ Adhesive should not be heated above 180°F.

Caution should be used when exposing M^3 Adhesive to an open flame.

Flashing: The flashing material **must** be a TAMKO polyester reinforced modified asphalt flashing material.

U.L. Requirements:

Contact TAMKO for information on U.L. systems requirements.

Caution: A product(s) in this specification contains crystalline silica and formaldehyde. Crystalline silica and formaldehyde have been classified as "known" human carcinogens by the International Agency for Research on Cancer (IARC) and the National Toxicology Program. A product(s) in this specification also contains oxidized asphalt. Occupational exposures to oxidized asphalt and its emissions during roofing have been classified by IARC as a "probable human carcinogen". Oxidized asphalt also contains Polycyclic Aromatic Hydrocarbons some of which have been classified by IARC as known or probable human carcinogens. The physical nature of the product(s) in this specification may help limit any inhalation or dermal hazard during application and/or removal.



102FR M³ AWAPLAN PREMIUM FR


INSULATED DECKS

However, physical forces such as sawing, grinding or drilling during demolition work and heating or burning may increase the inhalation or dermal exposure hazard of the product(s) in this specification. Take precautions to prevent breathing and contact with skin.



103FR M³ AWAPLAN PREMIUM FR

INSULATED DECKS



Material Requirements

TAMKO AWAPLAN VERS	A-SMOOTH	1 ply
TAMKO AWAPLAN PREM	IIUM FR	
(Granule Surfaced)		1 ply
M ³ Adhesive (Per 100 sq. ft.)	Approx. 1-1/2 to 2	-1/2 gal.

Slope: Positive drainage up to 3 in. per linear ft. **For slopes above 3/4 in. per linear ft.,** fastening of the AWAPLAN PREMIUM FR is required.

Deck: The deck should conform to TAMKO general requirements

Insulation: The insulation should be installed according to the manufacturer's specification in the thickness required. The insulation should conform to TAMKO requirements. Polyisocyanurate and expanded polystyrene must have an overlay of a minimum 1/2 in. fiberboard, perlite, or fiberglass roof insulation.

Adhesive: The adhesive **must** be TAM-PRO® M³ Adhesive.

AWAPLAN VERSA-SMOOTH: Starting at the low point of the roof, install 1 ply of TAMKO AWAPLAN VERSA-SMOOTH, beginning with a 1/2 m width, then a full 1 m width, side lapped 4 in. and end lapped 6 in. Apply at a right angle to the slope of the roof. The AWAPLAN VERSA-SMOOTH should be solidly adhered to the insulation with an application of M³ Adhesive at a rate not to exceed 1-1/2 to 2 gal per sq. for squeegee application and 1-1/2 to 2-1/2 gal. per sq. for spray application. Side laps and end laps shall be heat welded together.

Alternately, the AWAPLAN VERSA-SMOOTH may be solidly adhered to the insulation (pressed into the hot asphalt) with approximately 23 lbs. ($\pm 15\%$) of specification asphalt per 100 sq. ft. The asphalt should be above 400° F at the point of application and mopped no more than 4 ft. in front of the roll.

AWAPLAN PREMIUM FR: Starting at the low point of the roof, install 1 layer of TAMKO AWAPLAN PREMIUM FR granule surfaced sheet, side lapped 4 in. and end lapped 6 in. The AWAPLAN PREMIUM FR should be solidly adhered to the base ply with an application of M³ Adhesive at a rate not to exceed 1-1/2 to 2 gal. per sq. for squeegee application and 1-1/2 to 2-1/2 gal. per sq. for spray application. Side laps and end laps shall be heat welded together. **Use care when applying heat as damage can occur to the product by overheating.**

Using a 3/16" serrated edge squeegee will achieve an application rate of 1-1/2 gal. per sq. For spray application, the M³ Adhesive must be a minimum of 100°F at the spray tip. M³ Adhesive should not be heated above 180°F.

Caution should be used when exposing M³ Adhesive to an open flame.

Flashing: The flashing material **must** be a TAMKO polyester reinforced modified asphalt flashing material.

U.L. Requirements:

Contact TAMKO for information on U.L. systems requirements.

Caution: A product(s) in this specification contains crystalline silica. Crystalline silica has been classified as a "known" human carcinogen by the International Agency for Research on Cancer (IARC) and the National Toxicology Program. A product(s) in this specification also contains oxidized asphalt. Occupational exposures to oxidized asphalt and its emissions during roofing



103FR M³ AWAPLAN PREMIUM FR


INSULATED DECKS

have been classified by IARC as a "probable human carcinogen". Oxidized asphalt also contains Polycyclic Aromatic Hydrocarbons some of which have been classified by IARC as known or probable human carcinogens. The physical nature of the product(s) in this specification may help limit any inhalation or dermal hazard during application and/or removal. However, physical forces such as sawing, grinding or drilling during demolition work and heating or burning may increase the inhalation or dermal exposure hazard of the product(s) in this specification. Take precautions to prevent breathing and contact with skin.



104FR M³ AWAPLAN PREMIUM FR

INSULATED DECKS



Material Requirements

TAMKO AWAPLAN VERSA	AFLEX 1 ply
TAMKO AWAPLAN PREM	
(Granule Surfaced)	1 ply
M ³ Adhesive (Per 100 sq. ft.)	Approx. 1-1/2 to 2-1/2 gal.

Slope: Positive drainage up to 3 in. per linear ft. **For slopes above 3/4 in. per linear ft.,** fastening of the AWAPLAN PREMIUM FR is required.

Deck: The deck should conform to TAMKO general requirements.

Insulation: The insulation should be installed according to the manufacturer's specification in the thickness required. The insulation should conform to TAMKO requirements. Polyisocyanurate and expanded polystyrene must have an overlay of a minimum 1/2 in. fiberboard, perlite, or fiberglass roof insulation.

Adhesive: The adhesive must be TAM-PRO® M³ Adhesive.

AWAPLAN VERSAFLEX: Starting at the low point of the roof, install 1 ply of TAMKO AWAPLAN VERSAFLEX, beginning with a 1/2 m width, then a full 1 m width, side lapped 4 in. and end lapped 6 in. Apply at a right angle to the slope of the roof. The AWAPLAN VERSAFLEX should be solidly adhered to the insulation with an application of M³Adhesive at a rate not to exceed 1-1/2 to 2 gal per sq. for squeegee application and 1-1/2 to 2-1/2 gal. per sq. for spray application. Side laps and end laps shall be set in M³Adhesive. Care should taken to prevent damage to the system from water or wind prior to the cured adhesive sealing the laps.

Alternately, the AWAPLAN VERSAFLEX may be solidly adhered to the insulation (pressed into the hot asphalt) with approximately 23 lbs. $(\pm 15\%)$ of specification asphalt per 100 sq. ft. The asphalt

should be above 400° F at the point of application and mopped no more than 4 ft. in front of the roll.

AWAPLAN PREMIUM FR: Starting at the low point of the roof, install 1 layer of TAMKO AWAPLAN PREMIUM FR granule surfaced sheet, side lapped 4 in. and end lapped 6 in. The AWAPLAN PREMIUM FR should be solidly adhered to the base ply with an application of M³ Adhesive at a rate not to exceed 1-1/2 to 2 gal. per sq. for squeegee application and 1-1/2 to 2-1/2 gal. per sq. for spray application. Side laps and end laps shall be heat welded together. **Use care when applying heat as damage can occur to the product by overheating.**

Using a 3/16" serrated edge squeegee will achieve an application rate of 1-1/2 gal. per sq. For spray application, the M^3 Adhesive must be a minimum of 100°F at the spray tip. M^3 Adhesive should not be heated above 180°F .

Caution should be used when exposing M³ Adhesive to an open flame.

Flashing: The flashing material **must** be a TAMKO polyester reinforced modified asphalt flashing material.

U.L. Requirements:

Contact TAMKO for information on U.L. systems requirements.

Caution: A product(s) in this specification contains crystalline silica. Crystalline silica has been classified as a "known" human carcinogen by the International Agency for Research on Cancer (IARC) and the National Toxicology Program. A product(s) in this specification also contains oxidized asphalt. Occupational exposures to oxidized asphalt and its emissions during roofing have been classified by IARC as a "probable human carcinogen". Oxidized asphalt also contains Polycyclic Aromatic Hydrocarbons some of which have been classified by IARC as known or probable human carcinogens. The physical nature of the product(s) in this



104FR M³ AWAPLAN PREMIUM FR


INSULATED DECKS

specification may help limit any inhalation or dermal hazard during application and/or removal. However, physical forces such as sawing, grinding or drilling during demolition work and heating or burning may increase the inhalation or dermal exposure hazard of the product(s) in this specification. Take precautions to prevent breathing and contact with skin.



107FR M³ AWAPLAN PREMIUM FR

INSULATED DECKS



Material Requirements

TAMKO VERSA-BASE®	1 ply
TAMKO AWAPLAN PREMI	UM FR
(Granule Surfaced)	1 ply
M ³ Adhesive (Per 100 sq. ft.)	Approx. 1-1/2 to 2-1/2 gal.

Slope: Positive drainage up to 3 in. per linear ft. **For slopes above** 3/4 in. per linear ft., fastening of the AWAPLAN PREMIUM FR is required.

Deck: The deck should conform to TAMKO general requirements.

Insulation: The insulation should be installed according to the manufacturer's specification in the thickness required. The insulation should conform to TAMKO requirements. Polyisocyanurate and expanded polystyrene must have an overlay of a minimum 1/2 in. fiberboard, perlite, or fiberglass roof insulation.

Adhesive: The adhesive **must** be TAM-PRO® M³ Adhesive.

VERSA-BASE: Starting at the low point of the roof, install 1 ply of TAMKO VERSA-BASE, beginning with a 1/2 m width, then a full 1 m width, side lapped 2 in. and end lapped 4 in. Apply at a right angle to the slope of the roof. The VERSA-BASE should be solidly adhered to the insulation with an application of M³ Adhesive at a rate not to exceed 1-1/2 to 2 gal. per sq. for squeegee application and 1-1/2 to 2-1/2 gal. per sq. for spray application. Side laps and end laps shall be set in M³ Adhesive. Care should be taken to prevent damage to the system from water or wind prior to the cured adhesive sealing the laps.

Alternately, the VERSA-BASE may be solidly adhered to the insulation (pressed into hot asphalt) with approximately 23 bls. ($\pm 15\%$) of specification asphalt per 100 sq. ft. The asphalt should be above 400°F at the point of application and mopped no more than 4 ft. in front of the roll.

AWAPLAN PREMIUM FR: Starting at the low point of the roof, install 1 layer of TAMKO AWAPLAN PREMIUM FR granule surfaced sheet, side lapped 4 in. and end lapped 6 in. The AWAPLAN PREMIUM FR should be solidly adhered to the base ply with an application of M³ Adhesive at a rate not to exceed 1-1/2 to 2 gal. per sq. for squeegee application and 1-1/2 to 2-1/2 gal. per sq. for spray application. Side laps and end laps shall be heat welded together. Use care when applying heat as damage can occur to the product by overheating.

Using a 3/16" serrated edge squeegee will achieve an application rate of 1-1/2 gal. per sq. For spray application, the M³ Adhesive must be a minimum of 100°F at the spray tip. M³ Adhesive should not be heated above 180°F.

Caution should be used when exposing M³ Adhesive to an open flame.

Flashing: The flashing material **must** be a TAMKO polyester reinforced modified asphalt flashing material.

U.L. Requirements:

Contact TAMKO for information on U.L. systems requirements.

Caution: A product(s) in this specification contains crystalline silica and formaldehyde. Crystalline silica and formaldehyde have been classified as "known" human carcinogens by the International Agency for Research on Cancer (IARC) and the National Toxicology Program. A product(s) in this specification also contains oxidized asphalt. Occupational exposures to oxidized asphalt and its emis-



107FR M³ AWAPLAN PREMIUM FR


INSULATED DECKS

sions during roofing have been classified by IARC as a "probable human carcinogen". Oxidized asphalt also contains Polycyclic Aromatic Hydrocarbons some of which have been classified by IARC as known or probable human carcinogens. The physical nature of the product(s) in this specification may help limit any inhalation or dermal hazard during application and/or removal. However, physical forces such as sawing, grinding or drilling during demolition work and heating or burning may increase the inhalation or dermal exposure hazard of the product(s) in this specification. Take precautions to prevent breathing and contact with skin.



108FR M³ AWAPLAN PREMIUM

INSULATED DECKS



Material Requirements

TAMKO TAM-PLY IV®	
Fiberglass Ply Sheet	3 plies
TAMKO AWAPLAN PREMI	UM FR
(Granule Surfaced)	1 ply
Asphalt (Per 100 sq. ft.)	Approx. 69 lbs.
M ³ Adhesive (Per 100 sq. ft.)	Approx. 1-1/2 to 2-1/2 gal.

Slope: Positive drainage up to 3 in. per linear ft. **For slopes above** 3/4 in. per linear ft., fastening of the AWAPLAN PREMIUM FR is required.

Insulation: The insulation should be installed according to the manufacturer's specification in the thickness required. The insulation should conform to TAMKO requirements. Polyisocyanurate and expanded polystyrene must have an overlay of a minimum 1/2 in. fiberboard, perlite, or fiberglass roof insulation.

Deck: The deck should conform to TAMKO general requirements.

Asphalt: The asphalt should be certified by the manufacturer to meet ASTM D-312, **Type III for slopes up to 1/4 in.** and **Type IV for slopes up to 3 in.**

Adhesive: The adhesive **must** be TAM-PRO® M³ Adhesive.

Fiberglass Ply Sheets: Over the insulation, install 3 plies of TAMKOTAM-PLYIV in specification asphalt. Starting from the low point of the roof, apply a 1/3 m width, then a 2/3 m width. Follow with full 1 m widths, shingle fashion, lapping each ply $26^{15}/_{16}$ in. in such a manner so that at least 3 plies of ply sheet cover the insulation at any point. Approximately 23 lbs. (+15%) of specification asphalt per 100 sq. ft. should be used to embed each ply.

AWAPLAN PREMIUM FR: Starting at the low point of the roof, install 1 layer of TAMKO AWAPLAN PREMIUM FR granule surfaced sheet, side lapped 4 in. and end lapped 6 in. The AWAPLAN PREMIUM FR should be solidly adhered to the ply sheet with an application of M³ Adhesive at a rate not to exceed 1-1/2 to 2 gal. per sq. for squeegee application and 1-1/2 to 2-1/2 gal. per sq. for spray application. Side laps and end laps shall be heat welded together. **Use care when applying heat as damage can occur to the product by overheating.**

Using a 3/16" serrated edge squeegee will achieve an application rate of 1-1/2 gal. per sq. For spray application, the M³ Adhesive must be a minimum of 100°F at the spray tip. M³ Adhesive should not be heated above 180°F.

Caution should be used when exposing M³ Adhesive to an open flame.

Flashing: The flashing material **must** be a TAMKO polyester reinforced modified asphalt flashing material.

U.L. Requirements:

Contact TAMKO for information on U.L. systems requirements.

Caution: A product(s) in this specification contains formaldehyde. Formaldehyde has been classified as a "known" human carcinogen by the International Agency for Research on Cancer (IARC) and the National Toxicology Program. A product(s) in this specification also contains oxidized asphalt. Occupational exposures to oxidized asphalt and its emissions during roofing have been classified by IARC as a "probable human carcinogen". Oxidized asphalt also contains Polycyclic Aromatic Hydrocarbons some of which have been classified by IARC as known or probable human carcinogens. The physical nature of the product(s) in this specification may help limit any inhalation or dermal hazard during application and/or removal. However, physical forces such as sawing, grinding or drilling during demolition work and heating or burning may in-



108FR M³ AWAPLAN PREMIUM


INSULATED DECKS

crease the inhalation or dermal exposure hazard of the product(s) in this specification. Take precautions to prevent breathing and contact with skin.



109FR M³ AWAPLAN PREMIUM FR

INSULATED DECKS



Material Requirements

TAMKO TAM-GLASS PRE	MIUM®
Fiberglass Ply Sheet	1 ply
TAMKO VERSA-BASE®	
Modified Asphalt Base Sheet	1 ply
TAMKO AWAPLAN PREM	IUM FR
(Granule Surfaced)	1 ply
Asphalt (Per 100 sq. ft.)	Approx. 46 lbs.
M ³ Adhesive (Per 100 sq. ft.)	Approx. 1-1/2 to 2-1/2 gal.

Slope: Positive drainage up to 3 in. per linear ft. **For slopes above 3/4 in. per linear ft.,** fastening of the AWAPLAN PREMIUM FR is required.

Deck: The deck should conform to TAMKO general requirements.

Insulation: The insulation should be installed according to the manufacturer's specification in the thickness required. The insulation should conform to TAMKO requirements. Polyisocyanurate and expanded polystyrene must have an overlay of a minimum 1/2 in. fiberboard, perlite, or fiberglass roof insulation.

Asphalt: The asphalt should be certified by the manufacturer to meet ASTM D-312, Type III for slopes up to 1/4 in. and Type IV for slopes up to 3 in.

Adhesive: The adhesive must be TAM-PRO® M³ Adhesive.

TAM-GLASS PREMIUM: Starting at the low point of the roof, install 1 ply of TAM-GLASS PREMIUM, side lapped 2 in. and end lapped 4 in. Apply at a right angle to the slope of the roof. Solid mop to the insulation with approximately 23 lbs. (±15%) of specification asphalt per 100 sq. ft.

VERSA-BASE Sheet: Starting at the low point of the roof, install a 1/2 m width, then a full 1 m width of TAMKO VERSA-BASE, side lapped 2 in. and end lapped 4 in. Apply at a right angle to the slope of the roof. Solid mop to the base ply with approximately 23 lbs. ($\pm 15\%$) of specification asphalt per 100 sq. ft. The asphalt should be above 400° F at the point of application and mopped no more than 4 ft. in front of the roll.

Note: It is acceptable to invert the TAM-GLASS PREMIUM and the VERSA-BASE.

AWAPLAN PREMIUM FR: Starting at the low point of the roof, install 1 layer of TAMKOAWAPLAN PREMIUM FR granule surfaced sheet, side lapped 4 in. and end lapped 6 in. The AWAPLAN PREMIUM FR should be solidly adhered to the ply sheet with an application of M³Adhesive at a rate not to exceed 1-1/2 to 2 gal. per sq. for squeegee application and 1-1/2 to 2-1/2 gal. per sq. for spray application. Side laps and end laps shall be heat welded together. Use care when applying heat as damage can occur to the product by overheating.

Using a 3/16" serrated edge squeegee will achieve an application rate of 1-1/2 gal. per sq. For spray application, the M³ Adhesive must be a minimum of 100°F at the spray tip. M³ Adhesive should not be heated above 180°F.

Caution should be used when exposing M^3 Adhesive to an open flame.

Flashing: The flashing material **must** be a TAMKO polyester reinforced modified asphalt flashing material.

Caution: A product(s) in this specification contains crystalline silica and formaldehyde. Crystalline silica and formaldehyde have been classified as "known" human carcinogens by the International Agency for Research on Cancer (IARC) and the National Toxicology Program. A product(s) in this specification also contains oxidized asphalt. Occupational exposures to oxidized asphalt and its emis-



109FR M³ AWAPLAN PREMIUM FR


INSULATED DECKS

sions during roofing have been classified by IARC as a "probable human carcinogen". Oxidized asphalt also contains Polycyclic Aromatic Hydrocarbons some of which have been classified by IARC as known or probable human carcinogens. The physical nature of the product(s) in this specification may help limit any inhalation or dermal hazard during application and/or removal. However, physical forces such as sawing, grinding or drilling during demolition work and heating or burning may increase the inhalation or dermal exposure hazard of the product(s) in this specification. Take precautions to prevent breathing and contact with skin.



111FR M³ AWAPLAN PREMIUM FR

NAILABLE DECKS (GYPSUM AND LIGHTWEIGHT INSULATING CONCRETE)



Material Requirements

TAMKO VAPOR-CHAN®	
Fiberglass Venting Asphalt Base S	heet 1 ply
TAMKO AWAPLAN PREMIUM (Granule Surfaced)	FR 1 ply
M³ Adhesive (Per 100 sq. ft.) Appr	ox. 1-1/2 to 2-1/2 gal.
Clinch-type nails for base sheet (per 100 sq ft.)	Approx. 100 nails

Slope: Positive drainage up to 3 in. per linear ft. **For slopes above 3/4 in. per linear ft.,** fastening of the AWAPLAN PREMIUM FR is required.

Deck: The deck should conform to TAMKO general requirements

Adhesive: The adhesive must be TAM-PRO[®] M³ Adhesive.

VAPOR-CHAN: Starting at the low point of the roof, install 1 ply of TAMKO VAPOR-CHAN, beginning with a 1/2 m width, then a full 1 m width, side lapped 2 in. and end lapped 4 in. Apply at a right angle to the slope of the roof. Nail the sheets along the lap at intervals of no more than 8 in. Stagger-nail down the center of the sheet on 16 in. centers along 2 lines located 13 in. from each edge of the base sheet.

AWAPLAN PREMIUM FR: Starting at the low point of the roof, install 1 layer of TAMKO AWAPLAN PREMIUM FR granule surfaced sheet, side lapped 4 in. and end lapped 6 in. The field of the AWAPLAN PREMIUM FR membrane should be solidly adhered to the base sheet with an application of M³ Adhesive at a rate not to exceed 1-1/2 to 2 gal. per sq. for squeegee application and 1-1/2 to 2-1/2 gal. per sq. for spray application. Side laps and end laps shall be heat welded together. **Use care when applying heat as damage can occur to the product by overheating.**

Using a 3/16" serrated edge squeegee will achieve an application rate of 1-1/2 gal. per sq. For spray application, the M³ Adhesive must be a minimum of 100°F at the spray tip. M³ Adhesive should not be heated above 180°F.

Caution should be used when exposing M³ Adhesive to an open flame.

Flashing: The flashing material **must** be a TAMKO polyester reinforced modified asphalt flashing material.

U.L. Requirements:

Contact TAMKO for information on U.L. systems requirements.

Caution: A product(s) in this specification contains crystalline silica and formaldehyde. Crystalline silica and formaldehyde have been classified as "known" human carcinogens by the International Agency for Research on Cancer (IARC) and the National Toxicology Program. A product(s) in this specification also contains oxidized asphalt. Occupational exposures to oxidized asphalt and its emis-



111FR M³ AWAPLAN PREMIUM FR


NAILABLE DECKS (GYPSUM AND LIGHTWEIGHT INSULATING CONCRETE)

sions during roofing have been classified by IARC as a "probable human carcinogen". Oxidized asphalt also contains Polycyclic Aromatic Hydrocarbons some of which have been classified by IARC as known or probable human carcinogens. The physical nature of the product(s) in this specification may help limit any inhalation or dermal hazard during application and/or removal. However, physical forces such as sawing, grinding or drilling during demolition work and heating or burning may increase the inhalation or dermal exposure hazard of the product(s) in this specification. Take precautions to prevent breathing and contact with skin.



112FR M³ AWAPLAN PREMIUM FR

NAILABLE DECKS (WOOD)



Material Requirements

TAMKO TYPE 43 Coated Base Sheet, TAMKO
GLASS-BASE® or BASE-N-PLY® Base Sheet 1 ply
TAMKO AWAPLAN PREMIUM FR
(Granule Surfaced) 1 ply
M³ Adhesive (Per 100 sq. ft.) Approx. 1-1/2 to 2-1/2 gal.
Clinch-type nails
for base sheet (per 100 sq ft.) Approx. 100 nails

Slope: Positive drainage up to 3 in. per linear ft. **For slopes above** 3/4 in. per linear ft., fastening of the AWAPLAN PREMIUM FR is required.

Deck: The deck should conform to TAMKO general requirements

Adhesive: The adhesive must be TAM-PRO[®] M³ Adhesive.

Base Ply: Starting at the low point of the roof, install 1 ply of TAMKO TYPE 43 Coated Base Sheet, GLASS-BASE, or BASE-N-PLY, beginning with a 1/2 width, then a full width, side lapped 2 in. and end lapped 4 in. Apply at a right angle to the slope of the roof. Nail GLASS-BASE or BASE-N-PLY sheets along the lap at intervals of no more than 8 in. Stagger-nail on 16 in. centers along 2 lines located 13 in. from each edge of the base sheet. Nail TYPE 43 Coated Base Sheet along the lap at intervals of no more than 9 in. Stagger-nail on 18 in. centers along 2 lines located 12 in. from each edge of the base sheet. For specific fastening patterns for wind uplift listings, contact the Technical Services Department.

AWAPLAN PREMIUM FR: Starting at the low point of the roof, install 1 layer of TAMKO AWAPLAN PREMIUM FR granule surfaced sheet, side lapped 4 in. and end lapped 6 in. The field of the AWAPLAN PREMIUM FR membrane should be solidly adhered to the base sheet with an application of M³ Adhesive at a rate not to exceed 1-1/2 to 2 gal. per sq. for squeegee application and 1-1/2 to 2-1/2 gal. per sq. for spray application. Side laps and end laps shall be heat welded together. **Use care when applying heat as damage can occur to the product by overheating.**

Using a 3/16" serrated edge squeegee will achieve an application rate of 1-1/2 gal. per sq. For spray application, the M³ Adhesive must be a minimum of 100°F at the spray tip. M³ Adhesive should not be heated above 180°F.

Caution should be used when exposing M³ Adhesive to an open flame.

Flashing: The flashing material **must** be a TAMKO polyester reinforced modified asphalt flashing material.

U.L. Requirements:

Contact TAMKO for information on U.L. systems requirements.

Caution: A product(s) in this specification contains crystalline silica, formaldehyde and wood dust. Crystalline silica, formaldehyde and wood dust have been classified as "known" human carcinogens by the International Agency for Research on Cancer (IARC) and the National Toxicology Program. A product(s) in this specification also contains oxidized asphalt. Occupational



112FR M³ AWAPLAN PREMIUM FR


NAILABLE DECKS (WOOD)

exposures to oxidized asphalt and its emissions during roofing have been classified by IARC as a "probable human carcinogen". Oxidized asphalt also contains Polycyclic Aromatic Hydrocarbons some of which have been classified by IARC as known or probable human carcinogens. The physical nature of the product(s) in this specification may help limit any inhalation or dermal hazard during application and/or removal. However, physical forces such as sawing, grinding or drilling during demolition work and heating or burning may increase the inhalation or dermal exposure hazard of the product(s) in this specification. Take precautions to prevent breathing and contact with skin.



117 FR M³ AWAPLAN PREMIUM FR

NAILABLE DECKS (GYPSUM AND LIGHTWEIGHT INSULATING CONCRETE)



Material Requirements

•		
TAMKO VAPOR-CHAN®		
Fiberglass Venting Asphalt Ba	se Sheet	1 ply
TAMKO AWAPLAN VERSA-SI	MOOTH	1 ply
TAMKO AWAPLAN PREMI (Granule Surfaced)	UM FR	1 ply
M ³ Adhesive (Per 100 sq. ft.)	Approx. 1-1/2 to	2-1/2 gal.
Clinch-type nails for base sheet (per 100 sq ft.)	Approx.	100 nails

Slope: Positive drainage up to 3 in. per linear ft. **For slopes above 3/4 in. per linear ft.,** fastening of the AWAPLAN PREMIUM FR is required.

Deck: The deck should conform to TAMKO general requirements.

Adhesive: The adhesive **must** be TAM-PRO® M³ Adhesive.

VAPOR-CHAN: Starting at the low point of the roof, install 1 ply of TAMKO VAPOR-CHAN, side lapped 2 in. and end lapped 4 in. Apply at a right angle to the slope of the roof. Nail the sheets along the lap at intervals of no more than 8 in. Stagger-nail down the center of the sheet on 16 in. centers along 2 lines located 13 in. from each edge of the base sheet. For specific fastening patterns for wind uplift listings, contact the Technical Services Department.

AWAPLAN VERSA-SMOOTH: Starting at the low point of the roof, install 1 ply of TAMKO AWAPLAN VERSA-SMOOTH, beginning with a 1/2 m width, then a full 1 m width, side lapped 4 in. and end lapped 6 in. Apply at a right angle to the slope of the roof. The AWAPLAN VERSA-SMOOTH should be solidly adhered to the base sheet with an application of M^3 Adhesive at a rate not to exceed 1-1/2 to 2 gal per sq. for squeegee application and 1-1/2 to 2-1/2 gal. per sq. for spray application. Sides laps and end laps

shall be heat welded together.

Alternately, the AWAPLAN VERSA-SMOOTH may be solidly adhered to the base sheet (pressed into the hot asphalt) with approximately 23 lbs. ($\pm 15\%$) of specification asphalt per 100 sq. ft. The asphalt should be above 400° F at the point of application and mopped no more than 4 ft. in front of the roll.

AWAPLAN PREMIUM FR: Starting at the low point of the roof, install 1 layer of TAMKO AWAPLAN PREMIUM FR granule surfaced sheet, side lapped 4 in. and end lapped 6 in. The AWAPLAN PREMIUM FR should be solidly adhered to the base ply with an application of M³ Adhesive at a rate not to exceed 1-1/2 to 2 gal. per sq. for squeegee application and 1-1/2 to 2-1/2 gal. per sq. for spray application. Side laps and end laps shall be heat welded together. **Use care when applying heat as damage can occur to the product by overheating.**

Using a 3/16" serrated edge squeegee will achieve an application rate of 1-1/2 gal. per sq. For spray application, the M³ Adhesive must be a minimum of 100°F at the spray tip. M³ Adhesive should not be heated above 180°F.

Caution should be used when exposing M^3 Adhesive to an open flame.

Flashing: The flashing material **must** be a TAMKO polyester reinforced modified asphalt flashing material.

U.L. Requirements:

Contact TAMKO for information on U.L. systems requirements.

Caution: A product(s) in this specification contains crystalline silica and formaldehyde. Crystalline silica and formaldehyde have been classified as "known" human carcinogens by the International Agency for Research on Cancer (IARC) and the National Toxicology Program. A product(s) in this specification also contains oxidized asphalt. Occupational exposures to oxidized asphalt and its emis-

For complete information on TAMKO's recommendations and requirements, consult TAMKO's web site at www.tamko.com TAMKO Building Products, Inc., P. O. Box 1404, Joplin, MO 64802 • 1-800-641-4691 • www.tamko.com



117 FR M³ AWAPLAN PREMIUM FR

NAILABLE DECKS (GYPSUM AND LIGHTWEIGHT INSULATING CONCRETE)

sions during roofing have been classified by IARC as a "probable human carcinogen". Oxidized asphalt also contains Polycyclic Aromatic Hydrocarbons some of which have been classified by IARC as known or probable human carcinogens. The physical nature of the product(s) in this specification may help limit any inhalation or dermal hazard during application and/or removal. However, physical forces such as sawing, grinding or drilling during demolition work and heating or burning may increase the inhalation or dermal exposure hazard of the product(s) in this specification. Take precautions to prevent breathing and contact with skin.